



Valdisole 704-706 6th Street, Wynberg, Sandton, 2090
info@versuspaint.co.za | T: (011) 885 3136 | F: (011) 885 1719
www.versuspaint.co.za | www.paintwithapurpose.co.za | www.specifications.co.za

Versus Natural Stone Trowel VWNST

DESCRIPTION

Versus Natural Stone Trowel: A new generation of 100 % pure acrylic textured plaster finish. It uses stones (of various sizes) in a clear binder and no iron oxide pigments.

Versus Natural Stone Trowel is durable and flexible, aesthetically pleasing, maintenance free and has excellent adhesion.

- The product is body-color through Ultra Violet resistant
- Water resistant
- Allows the walls to breathe
- Versus Natural Stone Trowel assists in the hiding surfaces imperfections / blemishes in the substrate, due to its thickness (2,5mm)
- Retains its elasticity (0,5mm per 10 cm of coating)
- Environmentally friendly < 8 / l VOC (Volatile Organic Compounds).
- Water based
- Low odor

SURFACE PREPARATION

- Prepare substrate by removing all loose and friable matter.
- All surfaces need to be properly prepared / primed, as per manufactures specification**
- Ensure that the plaster surface is clean, dry and sound and in accordance with SABS 1514:1993 plaster specification and C.C.I – SANS 2001- EMI: 2007 SUCCESSFUL PLASTERING, (60s ACCURACY)

APPLICATION

- Versus Natural Stone Trowel is applied by steel trowel and leveled smooth.
- The product is a premixed, therefore no adding of water / thinning is required.
- Note: Thinning will result in color variations.
- Ensure that the product is well mixed prior to using, as settlement of the stone or separation may have occurred in transit.

SUITABLE SURFACES

- Versus Natural Stone Trowel is suitable for interior and exterior, wall and ceiling surfaces.
- It can be applied to the following surfaces: Cement Plaster, Concrete, Gypsum (Rhinolite), Steel, Glass, OSB Board, Fibre cement board (Nutec), Wood.
- It can also be applied onto any previously painted surfaces.

PACKAGING

- 35kg Pail or 300 KG DRUM

SPREAD RATE

- 5Kg / M²
- Note: Spread rates should be used as a guide only, as the actual spread rates will vary depending on the surface.

DRYING / CURING TIME

- 12- 24 Hours
- Note: Dependent on ventilation and other climatic conditions. Do not apply if rain is expected within 4 – 6 hours of application.

COLOUR RANGE

- The color is subject to stone availability from the supplier.

CLEANING SOLVENTS

- Water

ORDERS

- It is imperative that the correct quantity is ordered at the same time, to eliminate batch variance.
- Note: Versus Paint Specialists (Pty) Ltd cannot be held liable for any color variations, should insufficient quantities be ordered.
- Stone colors are subject to availability.
- Signed color sample panels are required prior to the manufacturing of product.

STORAGE

- Keep containers properly sealed.
- Always store the container away from direct heat or sunlight.
- Note: Keep out of reach of children

SHELF LIFE

- Minimum 12 Months, in an unopened container.

FIRE RATING

- This product is water based and non-flammable.
- It has the lowest fire rating and will only burn as long as there is a flame.

IMPORTANT

- All new, previously painted or unstable surfaces need to be primed / bonded with a suitable primer provided by Versus Paint Specialists (Pty) Ltd. (Please see preparation of surfaces)
- All horizontal surfaces need to be water-proofed; with Versus Versa-Proof (membrane is also recommended).

APPLICATION NOTES

- Do not apply in direct sunlight.
- Recommended maximum panel size recommended for application, is 10M².
- The entire panel is to be redone, should remedial work be required.
- Scaffold to be erected corner to corner, or from a v-joint to a v-joint, from a tape-joint to a tape-joint, or from a construction joint to a construction joint.
- Tape joints can be created, however they will need to be set out, marked, primed, painted with 2 coats Versus Aqua ripple and over coated in desired color, upon completion of coating application.

BEST RESULTS

- For best results, the product should be applied by an experienced applicator.