



Valdisole 704-706 6th Street, Wynberg, Sandton, 2090
info@versuspaint.co.za | T: (011) 885 3136 | F: (011) 885 1719
www.versuspaint.co.za | www.paintwithapurpose.co.za | www.specifications.co.za



Versus Roadline Paint VRMP

PRODUCT DESCRIPTION:

Solvent based road line paint made to meet the requirements of SANS SPEC731.

USES:

- Recommended for the marking of roadway, car parks and parking garages.
- Signwriting on roads.

FEATURES:

- Beaded product is used to improve night visibility by including beads or sprinkling beads onto the wet painted surfaces.
- Durability: Highly durable and UV resistant for the harsh South African climate.

PRODUCT INFORMATION:

Type: Modified Alkyd Resin.

- Appearance: Matt.
- Colors: White, Golden yellow, black and red.
- Solids: 61% by mass.
- Viscosity: 80 – 85 Krebs μ .
- Max VOC Level: 600g/l.
- Recommended Dry Film Thickness: 150 Microns.
- Flash Point: 2°C.

APPLICATION DETAILS:

- Mixing: Stir well before use.
- Method: Spray application as per equipment application. Specification for spray application Pressure Pot Graco Delta Gun 1.8mm.
- Brush can be used for small areas only.
- Thinning: If required Versus T. Thinner.
- Clean up: Versus T. Thinners.
- Spreading rate: 2 – 5 m²/l depending on surface porosity and profile.
- Conditions: Do not spray when the relative humidity is above 85%.
- Drying time: 2 hours.
- Recoating time: 4-6 hours.
- Requirements: 1 coat.

SURFACE PREPARATION:

- All Surfaces must be sound, clean and dry before painting and free from loose sand, oil, grease and other debris.

STORAGE:

- Keep containers properly sealed.
- Store away from direct heat, sun and severe cold.

PACKAGING:

- 5 Litres – 20 Litres – 200 Litres.

PRECAUTIONS:

- Detailed safety information: refers to the material safety data sheet for this product.
- Do not use excessive amount of thinners as this will degrade the durability of the coating.

DISCLAIMER

The above information is given in good faith but without warranty due to the fact that the methods of application, location and condition of the substrates being coated are beyond our control.