



Valdisole 704-706 6th Street, Wynberg, Sandton, 2090  
info@versuspaint.co.za | T: (011) 885 3136 | F: (011) 885 1719  
www.versuspaint.co.za | www.paintwithapurpose.co.za | www.specifications.co.za



## Versus Universal Undercoat VUC

### PRODUCT DESCRIPTION:

A solvent based interior and exterior general purpose undercoat for use under decorative topcoats.

### USES:

- Apply between primers and alkyd enamel topcoats on exterior interior wood, hardboard and metal.
- As a basecoat over correctly primed plaster to follow with enamel paint.
- Ideal for use on suitably primed interior and exterior surfaces.
- Apply between gloss enamels and emulsion topcoats, to improve intercoat adhesion for interior and exterior.

### FEATURES:

- Excellent sealing: Prevents absorption of more expensive top coats.
- Excellent adhesion.
- Provide a smooth base for topcoats
- Good levelling properties and easy brushing.

### PRODUCT INFORMATION:

- Type: Alkyd.
- Appearance: Matt/Low sheen.
- Colors: White and Pastel colors.
- Solids: 63-64% by mass.
- Density: 63% - 64%.
- Recommended Dry Film Thickness: 1 coat at minimum 30 µm and maximum 35µm.
- Viscosity at 25°C. : 30-35 Krebs µ. Secs. (Sheen Cup)
- Flash Point: 34°C.

### APPLICATION DETAILS:

- Mixing: Stir well before use.
- Method: Short nap mohair roller or brush.
- Thinning: Not recommended, but tap water if required. Thinning reduces the opacity.
- Clean up: Mineral Turpentine.
- Spreading rate: 8 – 10 m<sup>2</sup>/l depending on surface porosity and profile.
- Conditions: Avoid painting in wet or cold weather. Minimum temp 8° C
- Drying time: Touch dry 3-4 hours. Hard dry 16-18 hours at 25 degrees.
- Requirements: 1 coat

### SURFACE PREPARATION:

- New Surfaces must be sound, clean, dry and primed with an appropriate primer.
- Previously Painted Surfaces: Must be in sound condition. Apply 1 coat Versus Universal Undercoat and sand smooth after drying.

### STORAGE:

- Keep containers properly sealed.
- Store away from direct heat, sun and severe cold.

### PACKAGING:

- 5 Litres and 20 Litres.

### PRECAUTIONS:

- Detailed safety information: refers to the material safety data sheet for this product.
- Do not apply directly to unprimed surfaces.
- Drying times will be extended during wet or cold weather conditions.
- Must be over coated for protection.

### DISCLAIMER

The above information is given in good faith but without warranty due to the fact that the methods of application, location and condition of the substrates being coated are beyond our control.